


PA431
A68

BEST AVAILABLE COPY



97Y13620

In recognition of the importance of preserving what has been written, it is a policy of the American Institute of Physics to have books published in the United States printed on acid-free paper.

©1996 by American Institute of Physics
All rights reserved.
Printed in the United States of America.

Reproduction or translation of any part of this work beyond that permitted by Section 107 or 108 of the 1976 United States Copyright act without the permission of the copyright owner is unlawful. Requests for permission or further information should be addressed to the Office of Rights and Permissions, 500 Sunnyside Boulevard, Woodbury, NY 11797-2999; phone: 516-576-2268; fax: 516-576-2499; e-mail: rights@aip.org.

AIP Press
American Institute of Physics
500 Sunnyside Boulevard
Woodbury, NY 11797-2999

Library of Congress Cataloging-in-Publication Data
Physical properties of polymers handbook / editor, James E. Mark.
p. cm.
Includes bibliographical references and indexes.
ISBN 1-56396-295-0 (book)
ISBN 1-56396-598-4 (CD-ROM)
ISBN 1-56396-599-2 (set)
I. Polymers. I. Mark, James E., 1934-
TA455.P58P475 1996
620.1'92--dc20

95-50256
CIP

10 9 8 7 6 5 4 3 2 1

BEST AVAILABLE COPY

Common name	Acronym, alternate name	Class	Structure of repeat unit
Polyetheretherketone	PEEK	Polyketone	$\left[\text{O}-\text{C}_6\text{H}_4-\text{C}(=\text{O})-\text{C}_6\text{H}_4 \right]_n$
Polyethylene	PE	Polyolefin	$\left[\text{CH}_2-\text{CH}_2 \right]_n$ ✗
Poly(ethylene imine)		Polyamine	$\left[\text{CH}_2-\text{CH}_2-\text{NH} \right]_n$
Poly(ethylene oxide) [Poly(ethylene glycol)]	PEO (PEG)	Polyether	$\left[\text{CH}_2-\text{CH}_2-\text{O} \right]_n$
Polyethylene- terephthalate	PET	Polyester	$\left[(\text{CH}_2)_2-\text{O}-\text{C}(=\text{O})-\text{C}_6\text{H}_4-\text{C}(=\text{O}) \right]_n$ ✗
Polyglycine		Polypeptide	$\left[\text{NH}-\text{CH}_2-\text{C}(=\text{O}) \right]_n$
Poly(hexamethylene adipamide)	Nylon-66	Polyamide	$\left[\text{NH}-(\text{CH}_2)_6-\text{NH}-\text{C}(=\text{O})-(\text{CH}_2)_4-\text{C}(=\text{O}) \right]_n$
Polyhydroxybutyrate	PHB	Polyester	$\left[\text{O}-\overset{\text{CH}_3}{\underset{ }{\text{CH}}}-\text{CH}_2-\text{C}(=\text{O}) \right]_n$
Polyimide	PI	Polyimide	$\left[\text{N} \begin{array}{c} \text{O} \\ \parallel \\ \text{C} \\ \parallel \\ \text{O} \end{array} \text{C}_6\text{H}_2 \begin{array}{c} \text{O} \\ \parallel \\ \text{C} \\ \parallel \\ \text{O} \end{array} \text{N}-\text{C}_6\text{H}_4 \right]_n$
Poly(imino-1,3-phenylene iminoisophthaloyl) (Nomex)		Polyaramide	$\left[\text{HN}-\text{C}_6\text{H}_3-\text{NH}-\text{C}(=\text{O})-\text{C}_6\text{H}_3-\text{C}(=\text{O}) \right]_n$
Poly(imino-1,4-phenylene iminoterephthaloyl) (Kevlar)		Polyaramide	$\left[\text{HN}-\text{C}_6\text{H}_4-\text{NH}-\text{C}(=\text{O})-\text{C}_6\text{H}_4-\text{C}(=\text{O}) \right]_n$
Polyisobutylene	Butyl rubber	Vinylidene polymer	$\left[\overset{\text{CH}_3}{\underset{\text{CH}_3}{\text{C}}}-\text{CH}_2 \right]_n$
Polyisocyanate	PIC	Polyamide	$\left[\text{N} \begin{array}{c} \text{O} \\ \parallel \\ \text{C} \end{array} \text{R} \right]_n$
Polyisocyanide		Polyisocyanide	$\left[\text{N}-\text{R} \begin{array}{c} \parallel \\ \text{C} \end{array} \right]_n$